



**ALDEN, IOWA  
BALL DIAMOND DRY**

{Cross references with Unical-F}

---

**CHEMICAL ANALYSIS**

<u>Element</u>	<u>Typical* / Guaranteed</u>
<b>Calcium (Ca)</b>	<b>39.0% / 38.0%</b>
<b>Calcium Carbonate (CaCO<sub>3</sub>)</b>	<b>97.50% / 95.00%</b>
<b>Calcium (Ca) Min.</b>	<b>38.75%</b>
<b>Calcium (Ca) Max.</b>	<b>39.80%</b>

---

**RECOMMENDED APPLICATION**

See Diamond Dry brochure.

---

**SCREEN ANALYSIS\***

<u>U.S. Screen</u>	<u>% Passing</u>	<u>Average Particle Size*</u>	
6	99.5	U.S. Screen	10
16	7.0	Microns	2020
20	2.7	<i>* laser diffraction</i>	
40	1.2		

---

Bulk Density\*

Unpacked	81 lb/ft <sup>3</sup>
Packed	91 lb/ft <sup>3</sup>

\* These are typical analyses and are not intended to be guarantees.

(VIII)